

DURAL AQUA-DAM

HYDROPHOBIC POLYURETHANE GROUTING SYSTEM

A. R. Chambers Supply
111 Thirty-Fifth Street
Pittsburgh, PA 15201
412-681-8955

GROUTS

DURAL AQUA-DAM

Master Format #: 03 64 00

DESCRIPTION

DURAL AQUA-DAM is a hydrophobic polyurethane compound that is injected in concrete and other sound substrates to stop water from entering into occupied or unwanted places. The reaction time of the DURAL AQUA-DAM is controlled through the use of its accelerator, known as DURAL AQUACCELERATOR. DURAL AQUA-DAM forms a water tight seal within the substrate, that remains even after the water has subsided.

PRIMARY APPLICATIONS

- Leaking cracks and joints
- Water treatment facilities
- Wastewater treatment facilities
- Mines & tunnels
- Sewers & manholes
- Below grade walls subject to high water tables

FEATURES/BENEFITS

- ANSI/NSF 61 Certified
- Fast reaction time with added accelerator
- Very little shrinkage
- Excellent elongation to handle moving cracks and joints
- Bonds to wet and dry substrates
- Needs very little water to react and cure
- Remains active when the water subsides

TECHNICAL INFORMATION

TYPICAL PROPERTIES - LIQUID	RESULTS	TEST METHOD
Viscosity @ 77°F (25°C)	500 cps	ASTM D 1638
Specific Gravity	1.058	-
Physical State	Liquid	-
Color	Amber	-

TYPICAL PROPERTIES - CURED	RESULTS	TEST METHOD
Density	4 lb/ft ³ (64 kg/m ³)	ASTM D 1622
Elongation	40%	ASTM D 638
Tensile Strength	27 psi (0.19 MPa)	ASTM D 638
Shear Strength	16 psi (0.11 MPa)	ASTM C 273
Water Absorption	< 1% by volume	ASTM D 2842

TYPICAL REACTION PROFILE			
AQUACCELERATOR PERCENTAGE	0%	1.25%	2.5%
Initial Foam	Not Recommended	50 sec	15 seconds
Reaction Time	Not Recommended	3 min 20 sec	1 min 5 seconds

PACKAGING/YIELD

DURAL AQUA-DAM is packaged in 5 gal (19 L) pails and 55 gal (208 L) drums. DURAL AQUACCELERATOR is packaged in 1 pint (0.47 L) cans and 5 gal (19 L) pails. DURAL PUMP RINSE is packaged in 5 gal (19 L) pails only.



The Euclid Chemical Company

19218 Redwood Rd. • Cleveland, OH 44110
Phone: [216] 531-9222 • Toll-free: [800] 321-7628 • Fax: [216] 531-9596
www.euclidchemical.com

An **RPM** Company



SHELF LIFE

All materials have a 3 year shelf life in their original, unopened packages. Products are moisture sensitive and need to remain in airtight containers.

SPECIFICATIONS/COMPLIANCES

- ANSI/NSF 61

DIRECTIONS FOR USE

Surface & Crack Preparation: To ensure the project is completed properly, clean the exterior of the surface so that the full extent of the crack or joint can be seen. This will aid in proper hole drilling. Start by knowing the thickness of the concrete substrate that is to be repaired. This will be used in the spacing of packers. Starting at the lowest point of the crack; triangulate the position of the first hole to be drilled, so that it will intersect the crack at a 45° angle, half-way through the thickness of the concrete. Drill a 5/8" (16 mm) hole in this position and ensure that the bit used is long enough to pass through the crack. Drill the next hole in the same manner on the opposite side of the crack. The spacing between holes should be equal to the thickness of the concrete. Continue to drill holes in the same manner, moving up the crack until the entire length of the crack or joint has an equal chance of receiving the grout. Install 5/8" (16 mm) injection packers into the drilled holes and tighten. Inject water through the packers to make sure they don't leak around the sides. This water injection will also flush out any dust and debris that is in the crack due to the drilling process.

Mixing: Prior to injecting DURAL AQUA-DAM, properly stir the material and the accelerator. Do not use high speed mixing equipment, for that will "whip" air into the product. Pour the appropriate amount of DURAL AQUACCELERATOR into the DURAL AQUA-DAM and mix on slow speed for a minute or two, to ensure the accelerator is fully mixed in. The mixing ratios are as follows:

DURAL AQUA-DAM

DURAL AQUACCELERATOR

Package Size	Standard Amount	Minimum	Maximum
5 gal (19 L) Pail	16 oz. (0.47 L)	8 oz. (0.24 L)	32 oz. (0.94 L)
55 gal (208 L) Drum	1.25 gal (4.75 L)	80 oz. (2.4 L)	2.5 gal (9.5 L)

The standard mixing ratio should be used in most instances. Do not go below the minimum mixing amount, for the material will struggle to react, especially in colder weather. Do not add more than the maximum amount of accelerator for the material will face a great risk of shrinking, thus allowing water to pass through the crack or joint again.

Placement: Once the injection packers have been set and the drilled holes and crack have been flushed out with water, the injection of the material can begin. Start at the lowest point of a vertical crack and work upwards. Pump DURAL AQUA-DAM into the packer until foaming material comes out the face of the crack and starts to approach the next packer. On a horizontal crack, start at the end that was first installed and flushed with water. The more water left in the crack and injection site, the better. Move the injection head to the second packer and repeat until you have moved the entire length of the crack. A standard airless paint pump can be used for this application. Typical injection pressure into cracks is 200-3000 psi (1.4-20 MPa), depending on the width and depth of the crack. For large cracks and joints, oakum rope or a similar open celled structure device can be used to soak in DURAL AQUA-DAM and then placed into the crack or joint. Once the DURAL AQUA-DAM has cured, the packers can be removed or cut-off, flush with the surrounding surface. The grout that has cured outside of the face of the crack can be cut-back with a margin trowel or similar scraping tool. The packer holes can then be filled in with Euclid Chemical's Speed Plug hydraulic cement and finished as desired.

CLEAN-UP

Use all appropriate protective equipment. Avoid contact with the active grout. Use DURAL PUMP RINSE to clean out the lines of the injection equipment. DURAL PUMP RINSE can then be left in the lines as a primer, prior to the next project. Be sure to expel all DURAL PUMP RINSE from the lines prior to the next grouting job, for it will drastically affect the curing capability of the grout.

PRECAUTIONS/LIMITATIONS

- Colder temperatures will affect the viscosity and setting times of the product.
- Avoid exceeding 90°F (32°C) when warming product.
- Water used to react DURAL AQUA-DAM must be in the pH range of 3-10 for optimal performance.
- Store material in moisture free packaging. Atmospheric moisture may get to product causing a foam "head" inside of pail. This can be peeled off and the material below can still be usable.
- In all cases, consult the Material Safety Data Sheet before use.

Rev. 08.10