



Two-component, polymer-modified, cementitious leveling/pore sealing mortar plus FerroGard 901 penetrating corrosion inhibitor

DESCRIPTION

SikaTop 121 PLUS is a two component, polymer-modified, leveling and pore sealing mortar with the additional benefit of FerroGard 901, penetrating corrosion inhibitor. SikaTop 121 PLUS provides a smooth substrate, free of irregularities and bugholes for following protective coatings.

WHERE TO USE

- ▲ As a leveling/pore sealing mortar prior to protective coatings.
- ▲ On horizontal, vertical and overhead surfaces, interior and exterior.
- ▲ On grade, above and below grade, on concrete and mortar substrates.
- ▲ Block filler.
- ▲ Minor repair for gouges and broken edges.

ADVANTAGES

- ▲ Excellent adhesion to concrete and mortar substrates.
- ▲ High flexural and compressive strengths.
- ▲ Increased density - improved carbon dioxide resistance (carbonation) without adversely affecting water vapor transmission (not a vapor barrier).
- ▲ Increased freeze/thaw durability and resistance to deicing salts.
- ▲ Adds effective cover over rebars.
- ▲ Enhanced with FerroGard 901, a penetrating corrosion inhibitor - reduces corrosion even in the adjacent concrete.
- ▲ Compatible with coefficient of thermal expansion of concrete - Passes ASTM C-884 (modified).
- ▲ Can be applied over Sika FerroGard 903, corrosion inhibiting impregnation.
- ▲ Not flammable, non-toxic.

YIELD

0.4 cu. ft./unit

COVERAGE

One unit covers approximately 65 sq. ft. (6 m²) of smooth surface at 1/12 inch (2 mm) thickness.

PACKAGING

- Component 'A'** - 1 gal. plastic jug; 4/carton.
- Component 'B'** - 46.5 lb. multi-wall bag.

TYPICAL DATA FOR SIKATOP 121 PLUS (Material and curing conditions @ 73F (23C) and 50% R.H.)

SHELF LIFE	One year in original, unopened packaging.		
STORAGE CONDITIONS	Store dry at 40-95F (4-35C). Condition material to 65-75F before using. Protect Component 'A' from freezing; if frozen, discard.		
COLOR	Concrete gray when mixed.		
MIXING RATIO	Plant-proportioned kit. Mix entire unit.		
APPLICATION TIME	Approximately 45 min. after adding Component 'B' to Component 'A'. Application time is dependent on temperature and relative humidity.		
FINISHING TIME	45 to 60 min. after combining components; depends on temperature, relative humidity, and type of finish desired.		
FLEXURAL STRENGTH (ASTM C-293)			
28 days	2,000 psi		(13.8 MPa)
SPLITTING TENSILE STRENGTH (ASTM C-496)			
28 days	750 psi		(5.2 MPa)
BOND STRENGTH* (ASTM C-882 MODIFIED)			
28 days	2,000 psi		(13.8 MPa)
BOND STRENGTH PULL-OUT TEST (ACI 503R-30 MODIFIED)			
28 days	350 psi	(2.4 MPa)	Substrate failure
COMPRESSIVE STRENGTH (ASTM C-109)			
1 day	1,250 psi		(8.6 MPa)
7 days	5,000 psi		(34.5 MPa)
28 days	6,000 psi		(41.4 MPa)
PERMEABILITY (AASHTO T-277)			
28 days	Approximately 500 Coulombs		
CORROSION TESTING FOR FERROGARD 901			
Cracked Beam Corrosion Tests:	Reduced corrosion rates 63% versus control specimens.		
	ASTM G109 modified after 400 days		

* Mortar scrubbed into substrate.

HOW TO USE

SUBSTRATE

Concrete, mortar, and masonry products.

SURFACE PREPARATION

Remove all deteriorated concrete, dirt, oil, grease and all bond-inhibiting materials from the surface. Surface should be open-pore and textured (CSP-4). Saturate surface with clean water. Substrate should be saturated surface dry (SSD) with no standing water during application.

PRIMING

For priming of reinforcing steel use Sika Armatec 110 EpoCem (consult Technical Data Sheet).

Concrete Substrate:

Prime the prepared substrate with a brush or sprayed applied coat of Sika Armatec 110 EpoCem (consult Technical Data Sheet). Alternately, a scrub coat of SikaTop 121 Plus can be applied prior to placement of the mortar. The repair mortar has to be applied into the wet scrub coat before it dries.

MIXING

Pour approximately 4/5 of Component A into mixing container. Add Component B while continuing to mix. Mechanically mix with a low-speed drill (400-600 rpm) and paddle or appropriate-size mortar mixer. Mix to uniform consistency, maximum 3 minutes. Add remaining Component A to mix if a more loose consistency is desired.

Manual mixing can be tolerated only for less than a full unit.

APPLICATION & FINISH

SikaTop 121 *PLUS* can be applied by trowel, notched trowel, stiff bristle, or low pressure hopper gun. Work the material well into the prepared substrate, filling all pores and voids. As soon as the mortar layer starts to set, a uniform surface texture can be obtained by rubbing the surface with a fine sponge or a plastic trowel. Do not overwork SikaTop 121 *PLUS* during finishing and avoid the use of additional water.

CURING

As per ACI recommendations for portland cement concrete, curing is required. Protect the freshly applied mortar against direct sunlight, wind, frost and rain. Curing compounds adversely affect the adhesion of protective coatings. Therefore, do not use a water based curing compound, if the leveling mortar is going to be overcoated.

LIMITATIONS

- ▲ Application thickness:
 - Minimum 1/12 inch (2 mm)
 - Maximum 1/6 inch (4 mm)
- ▲ Minimum ambient and surface temperatures, 45F (7C) and rising at time of application.

CAUTION

Component 'A' - Irritant - May cause skin/eye/respiratory irritation. Avoid breathing vapors. Use with adequate ventilation. Avoid skin and eye contact. Safety goggles and rubber gloves are recommended.

Component 'B' - Irritant; suspect carcinogen - Contains portland cement and sand (crystalline silica). Skin and eye irritant. Avoid contact. Dust may cause respiratory tract irritation. Avoid breathing dust. Use only with adequate ventilation. May cause delayed lung injury (silicosis). IARC lists crystalline silica as having sufficient evidence of carcinogenicity in laboratory animals and limited evidence of carcinogenicity in humans. NTP also lists crystalline silica as a suspect carcinogen. Use of safety goggles and chemical resistant gloves is recommended. If PELs are exceeded, an appropriate, NIOSH/MSHA approved respirator is required. Remove contaminated clothing.

FIRST AID

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes, and contact a physician. For respiratory problems, remove person to fresh air.

CLEAN UP

In case of spillage, scoop or vacuum into appropriate container, and dispose of in accordance with current, applicable local, state and federal regulations. Keep container tightly closed and in an upright position to prevent spillage and leakage.

Mixed components: Uncured material can be removed with water. Cured material can only be removed mechanically.

Product Code 185. Sika, Armatex, SikaTop and FerroGard are registered trademarks. Made in USA. Printed in USA. March, 2000.

**KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION**

**KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY**

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

Sika warrants its products to be free from manufacturing defects and to meet Sika's current published properties when applied in accordance with Sika directions and tested in accordance with ASTM and Sika Standards. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product and excludes labor or the cost of labor. Any claim for breach of this warranty must be brought within one year of the date of purchase.

NO OTHER WARRANTIES EXPRESSED OR IMPLIED INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE SHALL APPLY. SIKA SHALL NOT BE LIABLE FOR ANY CONSEQUENTIAL OR SPECIAL DAMAGES OF ANY KIND, RESULTING FROM ANY CLAIM OF BREACH OF WARRANTY, BREACH OF CONTRACT, NEGLIGENCE OR ANY LEGAL THEORY. SIKA ASSUMES NO LIABILITY FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANOTHER'S PATENT.

Visit our website at www.sikausa.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers

For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Corregidora, Queretaro
C.P. 76920 A.P. 136
Phone: 52 42 25 0122
Fax: 52 42 25 0537